

Product Specification  
**Ground Granulated Blast Furnace Slag**

Chemical Analysis	
Element	Value
SiO <sub>2</sub>	36.00
Al <sub>2</sub> O <sub>3</sub>	15.50
Fe <sub>2</sub> O <sub>3</sub>	1.15
CaO	38.00
MgO	8.70
SO <sub>3</sub>	0.50
K <sub>2</sub> O	0.50
Na <sub>2</sub> O	0.50
Cl	0.020
S-2	1.30
Mn <sub>2</sub> O <sub>3</sub>	1.50
TiO <sub>2</sub>	1.40
L.O.I	0.25
I.R	0.50

Physical Analysis	
Element	Value
Blaine	4000
Residue on sieve 200 $\mu$	<0.20
Residue on sieve 90 $\mu$	<2.00

Note: This a typical specification. For your order, we'll send the specific one.